


shieldex



Shieldex® 125 µ Monofil

2002120125



Material	Polyamide / Nylon 6.6
Metal Plated	99.9 % Pure Silver
Yarn count raw	140/1± 8 dtex
Yarn count silverized	160/1± 6 dtex
Electrical Resistivity	<100 Ω/cm
Yield	62.500 m/kg ± 8 %
Tenacity	45± 6 cN/tex
Elongation / Break	30 % ± 6
Make Up	On cones 230 mm 3° 30
Packaging	Average 400 g net yarn per cone 15 or 30 cones per carton
Storage and Handling	According to our care and handling instructions
Compliance and Certification	OEKO-TEX® STANDARD 100; DIN EN ISO 9001:2015, REACH, RoHS

Alterations Reserved 26.09.24/07 – The above information has been compiled from our manufacturer area according to the latest state of development and application technology. Since application and further processing are beyond our control, no liability of the producer can be derived from the contents of the data sheet. All deviant or transcending data sheet information must be confirmed in written form by the manufacturer. Our general terms and conditions apply in all cases. All previous data sheets are invalid with the publication of this data sheet. Please note our handling and storage instructions as well accessible at www.shieldex.de.
