



Shieldex® 78/20 + OA

200121078200A



Material	Polyamide / Nylon 6
Metal Plated	99.9 % Pure Silver
+ OA Coating	Water-soluble finish
Yarn count raw	78/20 ± 3 dtex
Yarn count silverized	92/20 ± 3 dtex
Twist	Z 120
Electrical Resistivity	< 3.5 kΩ/m
Yield	105.000 m/kg ± 4 %
Tenacity	35 ± 7 cN/tex
Elongation / Break	33 % ± 8
Make Up	On cones 230 mm 3° 30
Packaging	Average 430 g net yarn per cone 15 or 30 cones per carton
Storage and Handling	According to our care and handling instructions
Compliance and Certification	DIN EN ISO 9001:2015, REACH, RoHS

Alterations Reserved 13.01.22/03 – The above information has been compiled from our manufacturer area according to the latest state of development and application technology. Since application and further processing are beyond our control, no liability of the producer can be derived from the contents of the data sheet. All deviant or transcending data sheet information must be confirmed in written form by the manufacturer. Our general terms and conditions apply in all cases. All previous data sheets are invalid with the publication of this data sheet. Please note our handling and storage instructions as well accessible at www.shieldex.de.
